

HARZ Labs Model Grey

Material Technical Data Sheet (TDS)

Version 1.2 / EN 13 April 2021



SECTION 1: DESCRIPTION AND APPLICATION

Model Gray is a durable, non-shrinking material designed for printing models with high requirements for physical and mechanical properties.

SECTION 2: MATERIAL PROPERTIES

2.1 Characteristics of liquid

Tested property	Standard/Method	Result (Metric)
Color	-	Grey
Odor	-	Weak
Density	ASTM D1298	$1.0 \pm 0.1 \text{ g/cm}^3$
Viscosity (25 °C)	ASTM D2393	750 ± 250 mPa∙s

2.2 Mechanical properties

Tested property	Standard/Method	Result (Metric)
Flexural Strength	ASTM D790	73.8 ± 3.7 MPa
Flexural Modulus	ASTM D790	1700 ± 200 MPa
Ultimate Tensile Strength	ASTM D638	41.8 ± 2.3 MPa
Elongation at Break	ASTM D638	6.2 ± 2.1 %
Hardness	ASTM D2240	80 ± 3 Shore D
IZOD Impact (Unnotched)	ASTM D4812	5.7 ± 0.2 kJ/m ²

2.3 Special parameters

Tested property	Standard/Method	Result
Solubility (24h)	ASTM D3132	≤ 0.01 %
Sorption (24h)	ASTM D570	≤ 0.47 %

The information above is believed to be accurate and represents the best information currently available to us. All test specimens were printed, cleaned, and post-processed per instructions provided by HARZ Labs company. Results provided here are representative of these processes and may vary if these established protocols are not followed. Users should make their own investigations to determine the suitability of the information for their particular purposes. In no event shall HARZ Labs LLC (OOO «XAPL Лабс») be liable for any claims, losses, or damages of any third party or for lost profits or any special, indirect, incidental, consequential or exemplary damages, howsoever arising, even if HARZ Labs LLC (OOO «XAPL Лабс») has been advised of the possibility of such damages.